



**Albi Manufacturing**  
Division of StanChem, Inc.  
401 Berlin St., East Berlin, CT 06023  
860/828-0571 Fax: 860/828-3297  
<http://www.albi.com>

**ALBI CLAD 800**  
**U.L. 1709 LISTINGS**

**COLUMNS: W10X49**

**FIRE TEST: UL 1709 HYDROCARBON**

<b>APPLICATION CONTOUR</b>	<b>U.L. DESIGN NO.</b>	<b>HOURLY RATING</b>	<b>MATERIAL THICKNESS</b>	<b>REINFORCEMENT</b>
	XR-602	1 hr.	.20 in. dry	wire mesh
	XR-602	1-1/2 hrs.	.41 in. dry	wire mesh
	XR-602	2 hrs.	.76 in. dry	wire mesh
	XR-607	1 hr.	.25 in. dry	none
	XR-608	1-1/2 hrs.	.35 in. dry	fiberglass ribbon
	XR-608	2 hrs.	.51 in. dry	fiberglass ribbon
	XR-609	2-1/2 hrs.	.62 in. dry	fiberglass ribbon
	XR-609	3 hrs.	.75 in. dry	fiberglass ribbon

**COLUMNS: 8 INCH PIPE**

**FIRE TEST: UL 1709 HYDROCARBON**

<b>APPLICATION CONTOUR</b>	<b>U.L. DESIGN NO.</b>	<b>HOURLY RATING</b>	<b>MATERIAL THICKNESS</b>	<b>REINFORCEMENT</b>
	XR-603	1 hr.	0.31 in. dry	wire mesh
	XR-603	1-1/2 hrs.	0.58 in. dry	wire mesh
	XR-603	2 hrs.	0.98 in. dry	wire mesh